

KESTER® EP256 SOLDER PASTE

No-Clean

DESCRIPTION

Kester EP256 Solder Paste is a no-clean, air or nitrogen reflowable, solder paste specifically designed for maximum robustness in reflow profiling and stencil printing. EP256 has the widest possible reflow processing window. EP256 is capable of stencil printing downtimes of up to 90 minutes with an effective first print down to 20 mils. EP256 is a solder paste formula that maintains its activity and printing characteristics for up to 8 hours without any shear thinning.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

- Stable wetting behavior over a wide range of profiles
- Capable of 90 minute break times in printing
- High print speeds to 200+ mm/sec (8+ in/sec)
- Compatible with enclosed print head systems
- Excellent printing characteristics to 0.4 mm (16 mil) pitch with Type 3 powder
- High activity on all substrates, including OSPs
- Capable of off-pad printing with no solder balls after reflow
- Stencil life: 8+ hours (process dependent)
- Scrap is reduced due to less paste dry out
- Stable tack over 8+ hours
- Classified as ROL1 per J-STD-004B

STANDARD APPLICATIONS

Stencil Printing: 90% Metal

Enclosed Head Printing: 90% Metal

ROHS COMPLIANCE

MacDermid Alpha does not determine any applicable Restriction of Hazardous Substances (RoHS) exemptions for our lead containing products at the user level.

TECHNICAL DATA

Category	Results	Procedure/Remarks	
Physical Properties (Data given for Sn63Pb37, 90% metal, -325+500 mesh)			
Viscosity (typical)	1400 poise	Malcom Viscometer @ 10 rpm and 25 °C	
Initial Tackiness (typical)	40 grams	Tested to Kester Method 1W-QC-3-04	
Slump Test	Pass	Tested to J-STD-005, IPC-TM-650, Method 2.4.35	
Solder Ball Test	Pass	Tested to J-STD-005, IPC-TM-650, Method 2.4.43	
Wetting Test	Pass	Tested to J-STD-005, IPC-TM-650, Method 2.4.45	
Reliability Properties			
Copper Mirror Corrosion	Low	Tested to J-STD-004, IPC-TM-650, Method 2.3.32	
Corrosion Test	Low	Tested to J-STD-004, IPC-TM-650, Method 2.6.15	
Electrochemical Migration (ECM)	Pass	Tested to J-STD-004B, IPC-TM-650, Method 2.6.14.1 Test Conditions: 65 °C, 85% RH, 25 days, 100V	
Fluorides by Spot Test	Pass	Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1	
Surface Insulation Resistivity (SIR)	Pass	Tested to J-STD-004B, IPC-TM-650, Method 2.6.3.7	
Surface Insulation Resistivity (SIR)	Pass	Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3	
		Blank	EP256
	Day 1	1.0*10 ¹⁰ Ω	9.8*10 ⁸ Ω
	Day 4	1.3*10 ¹⁰ Ω	1.6*10 ⁹ Ω
	Day 7	1.3*10 ¹⁰ Ω	1.1*10 ⁹ Ω

PROCESSING GUIDELINES

Printing Parameters



Squeegee Blade	Stainless Steel or 80 to 90 Durometer Polyurethane
Squeegee Speed	Capable to a maximum speed of 200 mm/sec (8 in/sec)
Stencil Material	Stainless Steel, Molybdenum, Nickel Plated, Brass
Temperature/Humidity	Optimal ranges are 21 to 25 °C (70 to 77 °F) and 35 to 65% RH

Recommended Reflow Profile

The recommended reflow profile for EP256 made with either the Sn63Pb37 or Sn62Pb36Ag02 is shown here. This profile is simply a guideline. Since EP256 is a highly active solder paste, it can solder effectively over a wide range of profiles, including lead-free profiles in some cases.

EP256 is capable of reflowing at the 235 °C peak temperatures required for fully collapsing lead-free SAC BGAs for maximum reliability and remains easy to clean after these high temperature profiles. Your optimal profile may be different from the one shown based on your oven, board and mix of components.

Contact MacDermid Alpha Technical Support if you need additional profiling advice.



Cleaning

EP256 is a no-clean formula. The residues don't need to be removed for typical applications. Although EP256 is designed for no-clean applications, its residues can be easily removed using automated cleaning equipment (in-line or batch) with a variety of readily available cleaning agents.

Storage, Handling and Shelf Life

Refrigeration is the recommended optimum storage condition for solder paste to maintain consistent viscosity, reflow characteristics and overall performance. EP256 should be stabilized at room temperature prior to printing. EP256 should be kept at standard refrigeration conditions, 0 to 10 °C (32 to 50 °F). Contact MacDermid Alpha Technical Support if you require additional advice with regard storage and handling of this material. Shelf life is 6 months from the date of manufacture when handled properly when held at 0 to 10 °C (32 to 50 °F).

AVAILABILITY

EP256 is commonly available in the Sn63Pb37, Sn62Pb36Ag2 and Sn43Pb43Bi14 alloys. Type 3 powder mesh is recommended, but different powder particle size distributions are available for standard and fine pitch applications. The appropriate combination depends on process variables and the specific application.

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.