

922-CX Soldering Flux

No-Clean, Low Solids, Liquid Flux

Product Description

Kester 922-CX Soldering Flux is a non-rosin organic fluxes designed for wave soldering conventional and surface mount circuit board assemblies. These fluxes eliminate defects often experienced in surface mount assembly wave soldering operations with traditional fluxes. These non-corrosive and non-conductive fluxes have an extremely low solids content. There is essentially NO RESIDUE left on the assembly after soldering. There are no residues to interfere with electrical testing and the expense of cleaning is eliminated. A particular feature of 922-CX is the very dry appearance of PCB assemblies as they exit the wave solder machine. Although cleaning is eliminated, the flux will not harm the electrical reliability of the assembly.

Performance Characteristics:

- Essentially no residue left behind after soldering
- Eliminates expense of cleaning
- Boards are dry as they exit the wave solder machine
- Non-corrosive and halogen-free
- No surface insulation resistance degradation
- No offensive odors given off during soldering
- Conforms to ANSI/J-STD-004, flux designator ORL0

RoHS Compliance

This product meets the requirement of the RoHS (Restriction of Hazardous Substances) Directive, 2002/95/EC Article 4 for the stated banned substances.

Physical Properties

Properties	922-CX	4662
Specific Gravity @ 24 °C (75 °F)	0.789	0.783
Pounds Per Gallon	6.58	6.53
Solids Content	2.3	---
Acid Number, mgKOH/gm	14.0 ± 0.7	---
Halogen Content	None	---
Flash point (T.O.C.)	18 °C (64 °F)	18 °C (64 °F)
Auto-ignition temperature	399 °C (750 °F)	399 °C (750 °F)

Properties	922-CX	4662
Copper Mirror Corrosion Test	Pass	---
Surface Insulation Resistance @ 50 °C (122 °F), 90% humidity*	10 ¹¹ ohm	---
Surface Insulation Resistance @ 85 °C (185 °F), 85%humidity**	10 ⁹ ohm	---
Thinner	4662	---
* Test Boards - 12.5 mil lines, 12.5 mil spaces. 50 volts DC bias. Reading taken after 60-sec charge of 100 volts DC with polarity reversed from bias voltage. SIR of unsoldered control = 1011 ohm.		
** Test Boards - 12.5 mil lines, 12.5 mil spaces. 50 volts DC bias. Reading taken after 60-sec charge of 100 volts DC with polarity reversed from bias voltage. SIR of unsoldered control = 109 ohm.		

Flux Application

922-CX can be applied to the assembly by dipping, spraying or wave fluxing. The usable preheat range is 82 to 110 °C (180 to 230 °F), but the optimum preheat temperature for most PCB assemblies is 99 to 110 °C (210 to 230 °F) as measured on the top or component side of the circuit board. Insufficient preheat tends to leave more residue behind after soldering. Excessive preheating time or temperature can partially degrade the flux and result in icicles or solder shorts.

Process Considerations

Control of the flux tank during use is necessary to assure a consistent amount of flux is applied to the circuit boards, the least amount of residue remains after soldering, no interference in electrical probe testing and consistent soldering results are obtained. Kester has developed the PS-22 Flux Test Kit to provide an effective means of determining the relative flux concentration and the proper amount of thinner to add to replace evaporative losses.

Also, debris from circuit boards (board fibers, etc.) and air lines can build up in the flux tank during use. When excessive, it will redeposit on circuit boards which may create a buildup of residues on probe test pins and can even affect the foam head characteristic in the flux tank. It is necessary to replace the flux tank with fresh flux when excessive debris accumulates in the flux tank.

Cleaning

This product is a no-clean flux. For most electronic assemblies, removal of the flux residue is not required. If post soldering residue removal is desired, it can be cleaned with a 2 to 5% concentration of a saponifier such as Kester 5768 Cleaner.

Recycling Services

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



Storage, Handling and Shelf Life

922-CX is flammable. Store away from sources of ignition. Shelf life is 3 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at this [link](#).

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.253.7837</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.