

## 2235 Soldering Flux

Organic Water-Soluble

---

### Product Description

Kester 2235 is a high activity 11% solids organic flux designed for automated soldering of circuit board assemblies where a more aggressive flux is required, but reliability considerations are paramount. 2235, a flux with comparably low solids in respect to other fluxes in the same category, will produce fewer skips on the bottom side surface mount pads. The residue after soldering is effectively removed in standard water cleaning systems. Although possessing high activity, boards exhibit high ionic cleanliness after water cleaning, exceeding the requirements of MIL-P-28809. No offensive odors or excessive smoke are emitted during soldering. The flux will not create excessive foaming in standard water cleaning systems. 2235 is classified as ORH1 under IPC J-STD-004.

### Performance Characteristics:

- Minimizes icicling and bridging
- Chemically compatible with most solder masks and board laminates
- Excellent choice for surface mount boards
- High ionic cleanliness and no surface insulation resistance degradation
- Classified as ORH1 under J-STD-004
- High activity

### RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive. Additional RoHS information is located at <https://www.kester.com/downloads/environmental>.

### Physical Properties

**Specific Gravity:** 0.856 ± 0.005

Anton Parr DMA @ 25 °C

**Flash Point:** 16 °C (60 °F)

**Percent Solids (Theoretical):** 11%

Tested to J-STD-004, IPC-TM-650, Method 2.3.34

## Reliability Properties

**Copper Mirror Corrosion:** High

**Corrosion Test:** High

Tested to J-STD-004, IPC-TM-650, Method 2.6.15

**Silver Chromate:** Fail

Tested to J-STD-004, IPC-TM-650, Method 2.3.33

**Chloride & Bromide:** 1.6%

Tested to J-STD-004A, IPC-TM-650, Method 2.3.35

**Fluorides by Spot Test:** Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

**Surface Insulation Resistant (SIR) IPC (Typical):** Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

	Blank	2235
Day 1	$7.9 \times 10^9 \Omega$	$9.7 \times 10^8 \Omega$
Day 4	$5.3 \times 10^9 \Omega$	$2.1 \times 10^9 \Omega$
Day 7	$4.7 \times 10^9 \Omega$	$2.6 \times 10^9 \Omega$

## Flux Application

2235 can be applied to circuit boards by a spray, foam or dip process. An air knife after the flux tank is recommended to remove excess flux from the circuit board and prevent dripping on the preheater surface.

## Process Considerations

The optimum preheat temperature for most circuit assemblies is 82 to 104 °C (180 to 220 °F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2 to 4 seconds. The wave soldering speed should be adjusted to accomplish proper preheating and evaporate excess solvent, which could cause spattering. For best results, speeds of 1.1 to 1.8 m/min (3.5 to 6 ft/min) are used. The surface tension has been adjusted to help the flux form a thin film on the board surface allowing rapid solvent evaporation.

## Flux Control

Specific gravity is normally the most reliable method to control the flux concentration. To check concentration, a hydrometer should be used. Control of the flux in the foam flux tank during use is necessary for assurance of consistent flux distribution on the circuit boards. The complex nature of the solvent system for the flux makes it imperative that Kester 4662 Thinner be used to replace evaporative losses. When excessive debris from circuit boards, such as board fibers and from the air-line build up in the flux tank, these particulates will redeposit on the circuit boards which may create a buildup of residues on probe test pins. It is, therefore, necessary to clean the tank and then replenish it with fresh flux when excessive debris accumulates in the flux tank.

## Cleaning

No neutralizer, saponifiers or detergents are necessary in the water wash system for complete removal of flux residues. It is not recommended to use high mineral content tap water. Otherwise, tap, deionized or softened water may be used for cleaning. The optimum water temperature is 54 to 66 °C (130 to 150 °F), although lower temperatures may be sufficient.

## Storage, Handling and Shelf Life

2235 is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

## Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

## Contact Information

To confirm this document is the most recent version, please contact [Assembly@MacDermidAlpha.com](mailto:Assembly@MacDermidAlpha.com)

<b>North America</b> 800 West Thorndale Avenue Itasca, IL USA 60143  Phone: +1 800.2.KESTER	<b>Asia Pacific</b> 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong  Phone: +852.3190.3100	<b>Europe</b> Ganghofer Strasse 45 82216 Gerlinden, Germany  Phone: +49 (0) 8142 4785 0
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "™" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.