

# 186 Soldering Flux

## Mildly Activated Rosin Liquid Flux

---

### Product Description

Kester 186 Soldering Flux, under MIL-F-14256, was QPL approved as Type RMA. The flux residue after soldering is non-corrosive and non-conductive. 186 rosin flux has been developed for use in critical applications where difficult assemblies are to be soldered, but process requirements stipulate use of Type RMA flux. This flux possesses high thermal stability for soldering multi-layer assemblies which may require a high preheat temperature or longer temperature dwell time. There is no surface insulation resistance degradation caused by the flux residue. The use of a minimum of ionic activating agents and the inactive nature of the residue permits leaving the residue on circuit board assemblies for many applications. The flux residue is also moisture and fungus resistant.

### Performance Characteristics:

- High thermal stability
- Improves soldering performance
- Eliminates the need and expense of cleaning
- Classified as ROL1 per J-STD-004, J-STD-004A & J-STD-004B

### RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive. Additional RoHS information is located at <https://www.kester.com/downloads/environmental>.

### Physical Properties

**Specific Gravity:** 0.879

Anton Paar DMA @ 25 °C

**Flash Point:** 18 °C (64 °F)

**Percent Solids (typical):** 36%

IPC-TM-650, Method 2.3.34

**Acid Number (typical):** 55 mg KOH/g flux

IPC-TM-650, Method 2.3.13

## Reliability Properties

**Copper Mirror Corrosion:** Low

IPC-TM-650, Method 2.3.32

**Corrosion Test:** Low

IPC-TM-650, Method 2.6.15

**Electrochemical Migration (ECM):** Pass

IPC-TM-650 Method 2.6.14.1 [65 °C, 85% RH, 100V, 21days]

**Surface Insulation Resistivity (SIR):** Pass

IPC-TM-650, Method 2.6.3.7

**Surface Insulation Resistivity (SIR):** Pass

IPC-TM-650, Method 2.6.3.3

## Flux Application

186 can be applied to circuit boards by a foam or dip process. An air knife after the flux tank is recommended to remove excess flux from the circuit board and prevent dripping on the preheated surface. A spray application can be used if the spray system can handle a high solids flux (36%).

## Process Considerations

The wave conveyor speed should be adjusted to achieve the contact time. Dwell time for Sn63Pb37 is typically 2 to 4 seconds. Contact time for lead-free alloys are typically 4 to 8 seconds. Adjust the preheat settings to achieve the proper preheat temperature. The optimum preheat temperature for most circuit assemblies is 90 to 105 °C (194 to 221 °F) as measured on the top or component side of the printed circuit board. This will be the same for all alloys.

## Flux Control

Specific gravity (0.879 ± 0.005 Anton Paar DMA @ 25 °C) is normally the most reliable method to control the flux concentration of rosin-based fluxes. To check concentration, a hydrometer should be used. Control of the flux in the foam flux tank during use is necessary for assurance of consistent flux distribution on the circuit boards. The complex nature of the solvent system for the flux makes it imperative that Kester 120 or Kester 4662 Thinner be used to replace evaporative losses. When excessive debris from circuit boards, such as board fibers and debris from the air line, build up in the flux tank, this debris and particulates will redeposit on the circuit boards which may create a buildup of residues on probe test pins. Therefore, it is necessary to clean the tank and then replenish it with fresh flux when excessive debris accumulates in the flux tank.

## Cleaning

186 residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, contact Kester Technical Support.

## Storage, Handling and Shelf Life

186 is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

## Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

## Contact Information

To confirm this document is the most recent version, please contact [Assembly@MacDermidAlpha.com](mailto:Assembly@MacDermidAlpha.com)

<b>North America</b> 800 West Thorndale Avenue Itasca, IL USA 60143  Phone: +1 800.2.KESTER	<b>Asia Pacific</b> 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong  Phone: +852.3190.3100	<b>Europe</b> Ganghofer Strasse 45 82216 Gernlinden, Germany  Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.