

979VT Soldering Flux

VOC-Free, No-Clean, Low Solids, Liquid Flux for Leaded and Lead-free Applications

Product Description

Kester 979VT Soldering Flux is a VOC-free, no-clean flux formulation for high quality, low-defect soldering of lead-free electronic circuit board assemblies. This flux's finely tuned activation system offers the best wetting available in VOC-free liquid flux technology and the shiniest solder joints. 979VT also reduces micro-solderballing on glossy and matte laminates and between connector pins. 979VT will not attack properly cured solder masks or FR-4 Epoxy-Glass laminate. It has been specially formulated to accommodate needs of single sided board assemblers. 979VT leaves no haze or visible residue behind, including the white powdery residue associated with use of earlier no-clean formulas.

Performance Characteristics:

- Biodegradable at pH of 2.0 or greater
- Chemically compatible with most solder masks and board laminates
- No surface insulation degradation
- No offensive odors
- Bright, shiny solder connections
- Classified as ORL0 under IPC JSTD-004 and ORM0 under IPC JSTD-004B

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2011/65/EU for the stated banned substances.

Physical Properties

Specific Gravity: 1.014 ± 0.005

Anton Paar DMA 35 @ 25 °C

Percent Solids (typical): 5%

Tested to J-STD-004, IPC-TM-650, Method 2.3.34

Acid Number: 43.0 ± 3.5mg KOH/g of flux

Tested to J-STD-004, IPC-TM-650, Method 2.3.13

pH (5% solution, typical): 3.2

Mettler-Toledo MA235 pH/Ions Analyzer@ 25 °C

Reliability Properties

Copper Mirror Corrosion:

No Breakthrough "L"

IPC J-STD-004B, IPC-TM-650, Method 2.3.32

Corrosion Test:

No Corrosion "L"

IPC J-STD-004, IPC-TM-650, Method 2.6.15B

Minor Corrosion "M"

IPC J-STD-004B, IPC-TM-650, Method 2.6.15C

Silver Chromate: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Chloride and Bromides: 0%

Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

Surface Insulation Resistance (SIR), IPC (typical): Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

Flux Application

979VT can be applied to circuit boards by a spray or dip process. It is not designed for a foam application. Flux deposition should be 120 to 240 μgr of solids/cm² (750 to 1500 μgr of solids/in²).

Process Considerations

The optimum preheat temperature for most circuit assemblies is 110 to 155 °C (230 to 311 °F), as measured on the top or component side of the assembly. Dwell time in the wave is typically 3 to 5 seconds for Sn63Pb37 and 4 to 8 seconds for lead-free alloys. The wave soldering conveyor speed should be adjusted to accomplish proper contact time for the alloy in the solder pot then the heaters in the preheat section adjusted to meet the requirements for the top side circuit board temperature.

Flux Control

Acid number is normally the most reliable method to control the flux concentration of low solids, no-clean fluxes. Evaporative loss is minimal because this flux is water-based. To check concentration, a simple acid-base titration should be used. PS-22 Test Kit and procedure are available from Kester. The thinner for this flux is DI water.

Cleaning

979VT flux residues are non-conductive and do not require removal in most applications. If residue removal is required, plain DI water at 43 to 54 °C (110 to 130 °F) may be used.

Storage, Handling and Shelf Life

Because this formulation is water-based, it is subject to freezing. A minimum storage temperature of 4 °C (40 °F) is recommended. If frozen, 979VT is easily reconstituted by stirring at room temperature. Shelf life is 1 year from the date of manufacture when handled properly and held at 4 to 25 °C (40 to 77 °F). 979VT will sometimes exhibit fluid darkening while in storage in its original container 8 to 12 weeks or longer after manufacture date. This flux in the container may change from a clear fluid to a light brown fluid. This is a normal change and does not affect the performance of 979VT.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

North America 800 West Thorndale Avenue Itasca, IL USA 60143 Phone: +1 800.2.KESTER	Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong Phone: +852.3190.3100	Europe Ganghofer Strasse 45 82216 Gernlinden, Germany Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.