

KESTER® 958 SOLDERING FLUX

Low-Solids, No-Clean Liquid Flux

DESCRIPTION

Kester 958 Soldering Flux is a no-clean, non-corrosive, zero-halogen liquid flux that is specifically designed for the wave soldering of conventional and surface mount circuit board assemblies. 958 was developed to give excellent soldering performance on bare copper printed circuit boards treated with OSP coatings. Essentially, no residue remains after soldering. Boards are dry and cosmetically clean as they exit the wave solder machine, thus posing no interference with electrical testing. 958 has excellent compatibility with most conformal coating products on the market today. This comprehensive formulation possesses improved wetting characteristics and also exhibits superior corrosion inhibiting properties and provides a non-tacky residue. A major advantage of this flux is the reduced odor associated with the soldering process.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

- Excellent for bare copper circuit board technology
- Compatible with conformal coat processes
- Improves soldering performance
- Reduced odor associated with soldering process
- Eliminates the need and expense of cleaning
- Non-corrosive tack-free residues
- Classified as ORL0 per J-STD-004
- Compliant to Bellcore GR-7

ROHS COMPLIANCE

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

TECHNICAL DATA

Category	Results		Procedure/Remarks	
Physical Properties				
Specific Gravity	0.806 ± 0.005		Anton Paar DMA 35 @ 25 °C	
Percent Solids (typical)	2.7		Tested to J-STD-004, IPC-TM-650, Method 2.3.34	
Acid Number	23.2 ± 1.0 mg KOH/g of flux		Tested to J-STD-004, IPC-TM-650, Method 2.3.13	
pH (10% solution)	3.1		Hanna Instruments 8314 @ 25 °C	
Reliability Properties				
Copper Mirror Corrosion	Low		Tested to J-STD-004, IPC-TM-650, Method 2.3.32	
Corrosion Test	Low		Tested to J-STD-004, IPC-TM-650, Method 2.6.15	
Silver Chromate	Pass		Tested to J-STD-004, IPC-TM-650, Method 2.3.33	
Chloride and Bromides	None Detected		Tested to J-STD-004, IPC-TM-650, Method 2.3.35	
Fluorides by Spot Test	Pass		Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1	
Surface Insulation Resistivity (SIR), IPC (Typical)	Pass		Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3	
		Blank	958 PD	958 PU
	Day 1	5.0*10 ⁹ Ω	3.1*10 ⁹ Ω	5.2*10 ⁹ Ω
	Day 4	5.8*10 ⁹ Ω	4.9*10 ⁹ Ω	6.8*10 ⁹ Ω
	Day 7	6.3*10 ⁹ Ω	5.5*10 ⁹ Ω	7.2*10 ⁹ Ω

FLUX APPLICATION

958 can be applied to circuit boards by a spray, foam or dip process. Flux deposition should be 120 to 240 μg of solids/ cm^2 (750 to 1500 μg of solids/ in^2). An air knife after the flux tank is recommended to remove excess flux from the circuit board and prevent dripping on the preheater surface for the Foam and Dip process.

PROCESSING GUIDELINES

The optimum preheat temperature for most circuit assemblies is 90 to 105 °C (194 to 221 °F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2 to 4 seconds for leaded alloys and 4 to 8 seconds for lead-free alloys. The conveyor speed should be adjusted to accomplish proper board contact time with the solder. Then the preheat temperatures are adjusted to achieve the required preheat top board temperatures. In the event you need further direction on the setup of your wave soldering system, please contact MacDermid Alpha Technical Support.

Flux Control

Acid number is normally the most reliable method to control the flux concentration of low solids, no clean fluxes. To check concentration, a simple acid-base titration should be used. PS-22 Test Kit and procedure are available from MacDermid Alpha.

Control of the flux in the foam flux tank during use is necessary for assurance of consistent flux distribution on the circuit boards. The complex nature of the solvent system for the flux makes it imperative that Kester 4662 Thinner be used to replace evaporative losses. When excessive debris from circuit boards, such as board fibers and from the airline build up in the flux tank, these particulates will redeposit on the circuit boards which may create a buildup of residues on probe test pins. It is, therefore, necessary to clean the tank and then replenish it with fresh flux when excessive debris accumulates in the flux tank.

Cleaning

958 flux residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, call MacDermid Alpha Technical Support.

Storage, Handling and Shelf Life

958 is flammable. Store away from sources of ignition. Shelf life is 3 years from date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.