

KESTER® BAF-1488HF

Halogen-Free Water-Soluble Ball Attach Flux

PRODCUT DESCRIPTION

Kester BAF-1488HF is a water-soluble tacky soldering flux formula with next generation halogen-free activator system (no intentionally added halogens). BAF-1488HF is designed to have high tackiness to minimize component movement and misalignment during reflow. Although BAF-1488HF is halogen-free, it has high soldering activity and can be a drop in replacement for a variety of metallurgies; such as typical tin-lead eutectic and the higher melting point alloys (SnAg, SnCu, SnAgCu, etc.). Post reflow the residues are completely soluble in water and do not require any cleaning additives.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PERFORMANCE CHARACTERISTICS

- Residue removal by hot DI water (~85°C)
- Truly Halogen-Free (no intentionally added halogens)
- Highly active
- Leaves bright/shiny solder joints after reflow
- ANSI/J-STD-004B flux anticipated ORH0
- Can reflow in air or nitrogen environments

RoHS COMPLIANCE

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

PHYSICAL PROPERTIES

Viscosity (typical): 310 poise

Tested to J-STD-004B, IPC-TM-650, Method 2.4.34.4

Tackiness (grams-force): 95 Typical

Kester Method #1W-QC-3-04

Acid Number: 30 - Typical

Tested to J-STD-004B, IPC-TM-650, Method 2.3.13

Quantitative Halides: None

Tested to J-STD-004B, IPC-TM-650 2.3.42

Quantitative Halogen: None

BS EN14582 (Halogen Analysis) O2 Bomb

Visual Appearance: Pale Yellow

Kester Method #1W-QC-G-18

RELIABILITY PROPERTIES**Copper Mirror Corrosion:** Low

Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Copper Corrosion: High

Tested to J-STD-004, IPC-TM-650, Method 2.6.15

ECM, IPC (typical): Pass

Tested to J-STD-004B, IPC-TM-650, Method 2.6.14.1

	Clean BAF-1488HF
96 hours	3.37*10 ⁶ Ω
596 hours	3.71*10 ⁶ Ω

SIR, IPC (typical): Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.7

	Blank	TSF-6522
Day 1	3.1*10 ¹⁰ Ω	2.6*10 ⁹ Ω
Day 4	1.3*10 ¹⁰ Ω	4.2*10 ¹⁰ Ω
Day 7	8.8*10 ¹⁰ Ω	6.4*10 ¹⁰ Ω


STANDARD APPLICATIONS

BAF-1488HF Tacky solder flux formulations are designed for stencil/screen printing, pin transfer and dipping applications. Tacky solder flux formulations can be used as a tack and flux vehicle for soldering components to a solid solder deposit (SSD), Ball grid array (BGA) ball attach, Chip Scale packages or precision pad technology (PPT) board surfaces. Great for rework

applications on all PCB packages.

RECOMMENDED REFLOW PROFILE

The recommended convection reflow profile for Sn96.5Ag3.5, Sn99.3Cu0.7, or the various SnAgCu alloys is shown here. This profile is simply a guideline. As BAF-1488HF was engineered to be a versatile, robust interconnect material other reflow profiles will be effective. The optimal profile for a process may be different from the one shown based on oven type, component design, fixturing and mix of defects. Please contact Kester if additional profiling advice is needed. BAF-1488HF will facilitate excellent wetting in an air reflow environment and can also be used in an inert (nitro-gen) environment.



CLEANING

BAF-1488HF residues are best removed using automated cleaning equipment (in-line or batch). A de-ionized water final rinse is recommended. Water temperatures should be $\sim 80^{\circ}\text{C}$, with water pressure of 45 to 65 psi. For best results, flux residues should be removed as soon as possible, preferably within 4 hours after soldering. Assemblies should be checked for ionic cleanliness levels to maintain the highest standards possible. IPC J-STD-001 specifies a maximum of 1.56 micro-grams/cm² NaCl equivalent when tested in accordance with IPC-TM-650, Test Method 2.3.25 or 2.3.26.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

STORAGE

BAF-1488HF should be kept at standard refrigeration conditions, 0-10°C (32-50°F). BAF-1488HF should be stabilized at room temperature prior to printing. Please contact Kester if you require additional advice with regard to storage and handling of this material. Shelf life study is still ongoing but we anticipate minimum 6 months shelf life from date of manufacture in room temperature and handled properly.

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 14 Joo Koon Crescent, Singapore 629014 65.6430.0700
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.