

KESTER® 1429 SOLDERING FLUX

VOC-Free, Organic, Water Soluble Liquid Flux

DESCRIPTION

Kester 1429 Soldering Flux, a VOC-free, organic, water soluble flux, is a self-neutralizing type of flux formulation based on research work originally performed at the Battelle Memorial Institute. The unique chemistry of 1429 flux provides for self-neutralization through a time/temperature relationship which results in a residue which is neutral and non-corrosive when properly heated. As with any organic flux, excessive heating can cause the flux to char and decrease both fluxing ability and removability. The surface tension of 1429 flux has been adjusted to promote solder flow, prevent icicling and bridging and obtain a bright soldered surface. As with any MacDermid Alpha flux formulation, 1429 is manufactured under strict quality control requirements for consistent performance and assured reliability.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

- High activity
- Minimizes icicling and bridging
- High ionic cleanliness and no surface insulation resistance degradation
- Classified as ORH1 per J-STD-004

TECHNICAL DATA

Category	Results	Procedure/Remarks
PhysProperties		
Specific Gravity	1.061 ± 0.010	Antoine Paar DMA 35 @ 25 °C
Percent Solids (Typical)	18	Tested to J-STD-004, IPC-TM-650, Method 2.3.34
Reliability Properties		
Copper Mirror Corrosion	High	Tested to J-STD-004, IPC-TM-650, Method 2.3.32
Corrosion Test	High	Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Category	Results	Procedure/Remarks
Silver Chromate	Fail	Tested to J-STD-004, IPC-TM-650, Method 2.3.33
Chloride and Bromides	2.3%	Tested to J-STD-004, IPC-TM-650, Method 2.3.35
Fluorides by Spot Test	Pass	Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

FLUX APPLICATION

1429 can be applied by a spray, dip, or wave process.

PROCESSING GUIDELINES

1429 Organic Flux is designed for tinning and dipping operations where a more active flux than rosin is required, inorganic acid fluxes are too corrosive and the ease of removing the residue with water is desired. For some applications the flux can be diluted to half strength with distilled, deionized or softened tap water. This further decreases tinning costs. 1429 flux can be used effectively without preheating.

Insulated Wires: This is not recommended for tinning of insulated wire because raw flux will wick up under the insulation and become trapped. This can lead to corrosion of the wire over time.

Bellows: Avoid using this flux for soldering of bellows and other closed assemblies where residues which have not been completely neutralized can be trapped and lead to deterioration of soldered joints over time.

Flux Control

Specific gravity is normally the most reliable method to control the flux concentration. To check concentration, a hydrometer should be used. DI water can be used to replace evaporative losses.

Cleaning

No neutralizer, saponifiers or detergents are necessary in the water wash system for complete removal of flux residues. It is not recommended to use high mineral content tap water. Otherwise, tap, deionized or softened water may be used for cleaning. The optimum water temperature is 45 to 65 °C (113 to 140 °F), although lower temperatures may be sufficient.

Storage, Handling and Shelf Life

Because this formulation is water based, it is subject to freezing. A minimum storage temperature of 4 °C (40 °F) is recommended. If frozen, 1429 is easily reconstituted by stirring at room temperature. Shelf life is 2 years from date of manufacture when handled properly and held at 4 to 25 °C (40 to 77 °F).

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.