

SELECT-10™ Selective Solder Flux

Zero-Halogen, No-Clean

Product Description

Kester SELECT-10™ Selective Solder Flux is a zero-halogen, no-clean, liquid flux designed specifically for the needs of the selective soldering process. Sustained activity within the flux allows for good barrel fill in challenging applications, such as reflowed copper OSP boards or with difficult to solder components. Specific to selective soldering, SELECT-10™ does not spread beyond the spray pattern and will not clog the fluxer head. SELECT-10™ residues are non-tacky for improved cosmetics. SELECT-10 is classified as ROL0 flux under IPC J-STD-004B. SELECT-10™ is classified as ROL0 per IPC J-STD-004B. SELECT-10™ is also available as a flux-pen. For a list of compatible products, visit Kester' website or con- tact Kester Technical Support.

Performance Characteristics:

- Zero-halogen (none intentionally added)
- Provides good solderability under air atmosphere
- Controlled flux application, flux does not spread beyond the spray pattern
- Non-corrosive, non-conductive and non-tacky residues
- Ability to provide desired hole-fill with preheat temperatures over 140 °C
- No clogging
- Compliant to GR-78-CORE (Telcordia/Bellcore)
- Classified as ROL0 per J-STD-004B
- Pass SIR in raw and preheating condition
- Also available as a flux-pen

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive. Additional RoHS information is located at <https://www.kester.com/downloads/environmental>.

Physical Properties

Specific Gravity @ 25°C: 0.835 (typical)

Acid Number (typical): 40.0 mg KOH/g flux

Percent Solids (theoretical): 10%

Reliability Properties

Copper Mirror Corrosion: Low

Tested to J-STD-004B, IPC-TM-650, Method 2.3.32

Corrosion Test: Low

Tested to J-STD-004B, IPC-TM-650, Method 2.6.15

Bono Corrosion Test: Pass; Fc=1.05%

Test Conditions: 85 °C, 85% RH, 15 days, 12V

Halogen Content: None Detected

Tested to J-STD-004B, IPC-TM-650, Method 2.3.28.1

Bellcore SIR, IPC: Pass; All Readings $>2.0 \times 10^{10} \Omega$

Tested to GR-78 13.1.3

Test Conditions: 35 °C, 85% RH, 4 days, 100V

Board Prepare Conditions: Room Temperature: Dry with 80 °C Preheating. Pattern up through by soldering process, pattern down through by soldering process

Electrochemical Migration (ECM): Pass

Tested to J-STD-004B, IPC-TM-650, Method 2.6.14.1

Test Conditions: 65 °C, 90% RH, 25 days, 100V

Board Prepare Conditions: Room Temperature: Dry with 80 °C Preheating. Pattern up through by soldering process, pattern down through by soldering process

Surface Insulation Resistance (SIR): Pass; All Readings $> 1.0 \times 10^8 \Omega$

Tested to J-STD-004B, IPC-TM-650, Method 2.6.3.7

Test Conditions: 40 °C, 90% RH, 7 days, 12.5V

Board Prepare Conditions: Room Temperature: Dry with 80 °C Preheating. Pattern up through by soldering process, pattern down through by soldering process

Surface Insulation Resistance (SIR): Pass

Tested to J-STD-004A, IPC-TM-650, Method 2.6.3.3

Test Conditions: 85 °C, 85% RH, 7 days, 100V

Board Prepare Conditions: Room Temperature: Dry with 80 °C Preheating. Pattern up through by soldering process, pattern down through by soldering process

Flux Application

SELECT-10™ is designed for a drop jet fluxer or ultrasonic fluxer in selective solder applications. Flux deposition should be 186 to 465µgr/cm² (1200 to 3000µgr/in²) of solids. SELECT-10™ Flux-Pen® is applied to circuit boards via Flux-Pen® for rework.

Process Considerations

Circuit Board Process Recommendations	
Printing Process Parameters	Recommendations
Flux deposition	186 to 465µgr/cm ² (1200 to 3000µgr/in ²) of solids
Top side board temperature (bottom preheaters only)	90 to 140 °C (194 to 284 °F) Maximum bottom side board temperature 145 °C
Top side board temperature (top preheaters only)	90 to 145 °C (194 to 293 °F)
Top side board temperature (bottom and top preheaters) ¹	90 to 140 °C (194 to 284 °F) Maximum bottom side board temperature 145 °C
Recommended preheat profile	Straight ramp to top side board temperature
Solder contact time	2.5 to 6 seconds
Maximum soldering time in the soldering module with pre-heat at 125 °C	2+ hours
Solder bath temperature ²	280 to 320 °C (536 to 608 °F) for SnCu or SAC alloy 260 to 300 °C (500 to 572 °F) for Sn63Pb37 alloy

¹ Board is heated from top and bottom there will be a smaller delta temperature between the top and bottom of the board and minimizing the risk of sublimation. Caution: Using top and bottom preheaters simultaneously does not ensure the center of the board reach proper temperature for soldering.

² The solder bath temperature is a function of the solder nozzle size, circuit board design and components.

Above information is a guideline and it is advisable to note that the optimum settings for a given assembly may vary and this is dependent on the circuit board design, board thickness, components used and equipment used. A design of experiment is recommended to be done to optimize the soldering process.

SELECT-10™ Flux-Pen® should only be applied to areas that will be fully heated by the soldering iron or other reflow tool. Care should be taken to avoid flooding the assembly. The surface tension has been adjusted to help the flux form a thin film on the board surface allowing rapid solvent evaporation.

Flux Control

SELECT-10™ is designed to be sprayed with a drop jet fluxer or ultrasonic fluxer. Incoming solderability inspection of circuit boards and components is advisable as a part of process control to maintain consistent soldering results.

Cleaning

SELECT-10™ residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required it can be removed using commercially available flux residue cleaner. Contact Kester Technical Support for additional assistance.

Recycling Services

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



Storage, Handling and Shelf Life

SELECT-10™ is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at this [link](#).

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.253.7837</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.