

# **KESTER® 1544 SOLDERING FLUX**

# **Activated Rosin Liquid Flux**

## **DESCRIPTION**

Kester 1544 Soldering Flux is a homogeneous solution of high quality, purified Grade WW rosin blended into an alcohol solvent system. A very effective activating agent has been added to provide superior fluxing ability. 1544 is a liquid equivalent of Kester 44 Activated Rosin Core Solder. The desired flux activity and the amount of rosin residue are determined by the concentration (solids percentage) of the flux.1544 has been developed for fluxing applications where non-activated and mildly activated rosin fluxes are too inactive to remove metal oxides, where proper and complete residue removal of potentially corrosive water soluble organic acid flux is not possible, and where soldering of electronic assemblies requires instant wetting and excellent capillary flow. 1544 can be used for solder coating or tinning bare leads.

#### READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

#### **FEATURES & BENEFITS**

- High thermal stability
- Improves soldering performance
- Classified as ROM1 per J-STD-004

# **ROHS COMPLIANCE**

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive.

#### **TECHNICAL DATA**

Category	Results	Procedure/Remarks	
Physical Properties			
Specific Gravity	0.917 to 0.928	Anton Paar DMA @ 25 °C	
Percent Solids (typical)	50%	Tested to J-STD-004, IPC- TM-650, Method 2.3.34	
Flash Point	18 °C (64 °F)		
VOC Content (g/liter)	459		





# **TECHNICAL DATA SHEET**

Category	Results	Procedure/Remarks	
Reliability Properties			
Copper Mirror Corrosion	Moderate	Tested to J-STD-004, IPC- TM-650, Method 2.3.32	
Corrosion Test	Low	Tested to J-STD-004, IPC- TM-650, Method 2.6.15	
Silver Chromate	Fail	Tested to J-STD-004, IPC- TM-650, Method 2.3.33	
Chloride and Bromides	0.44%	Tested to J-STD-004, IPC- TM-650, Method 2.3.35	
Fluorides by Spot Test	Pass	Tested to J-STD-004, IPC- TM-650, Method 2.3.35.1	

#### **FLUX APPLICATION**

1544 can be applied by brush, dip or wave processes.

## **PROCESSING GUIDELINES**

The optimum preheat temperature for most circuit assemblies is 90 to 105 °C (194 to 221 °F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2 to 4 seconds for leaded soldering process and 4 to 8 seconds for a lead-free process. The wave soldering speed should be adjusted to accomplish the proper solder contact range. The next step will be to adjust the temperature settings for the preheat section to achieve the proper preheat temperatures range as measured on the topside of the circuit board.

# **Flux Control**

Specific gravity is normally the most reliable method to control the flux concentration of high solids rosin-based fluxes. To check concentration, a hydrometer should be used. Kester 104 Thinner is an appropriate solvent for diluting this activated rosin flux to the desired solids content and viscosity, and for restoring solvent loss through evaporation. The correct specific gravity range for 1544 is 0.917 to 0.928 (Anton Paar DMA @ 25 °C).

## Cleaning

1544 residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, call MacDermid AlphaTechnical Support.





# **TECHNICAL DATA SHEET**

# Storage, Handling and Shelf Life

1544 is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

## **RECYCLING SERVICES**

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



## **SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.** 

#### **CONTACT INFORMATION**

#### www.macdermidalpha.com

North America
140 Centennial Avenue
Piscataway, NJ 08854
1.800.367.5460

**Europe**Unit 2, Genesis Business Park
Albert Drive
Woking, Surrey, GU21 5RW, UK
44.01483.758400

Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indicent, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDemid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or

