

KESTER® 2220-VF SOLDERING FLUX

VOC-Free, Organic, Water Soluble Liquid Flux

DESCRIPTION

Kester 2220-VF Soldering Flux is a high-activity, organic flux designed for lead-free automated wave solder applications. The flux will provide maximum capillary wetting action up plated through-holes, making it ideal for use on multilayer boards. Along with this enhanced activity, 2220-VF flux produces bright, shiny solder joints and the residue after soldering is effectively removed in standard water cleaning systems.

2220-VF is free of volatile organic compounds (VOCs), which provides optimal heat stability for the lead-free wave soldering process. The use of VOC-free solvents eliminates the use of ozone depleting chemicals which results in an environmentally friendly process.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

- Thermally stable and VOC-free to allow for effective high temperature soldering
- Chemically compatible with most solder masks and board laminates
- Compatible with leaded and lead-free wave soldering applications
- High activity
- Minimizes icicling and bridging
- High ionic cleanliness and no surface insulation resistance degradation
- Classified as ORH1 per J-STD-004

ROHS COMPLIANCE

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive.

TECHNICAL DATA

Category	Results	Procedure/Remarks
Physical Properties		
Specific Gravity	1.060	Anton Paar DMA 35 @ 25 °C
Percent Solids (typical)	7%	Tested to J-STD-004, IPC-TM-650, Method 2.3.34
Thinner	DI Water	
Reliability Properties		
Copper Mirror Corrosion	High	Tested to J-STD-004, IPC-TM-650, Method 2.3.32
Corrosion Test	High	Tested to J-STD-004, IPC-TM-650, Method 2.6.15
Silver Chromate	Fail	Tested to J-STD-004, IPC-TM-650, Method 2.3.33
Chloride and Bromides	2.4%	Tested to J-STD-004, IPC-TM-650, Method 2.3.35
Fluorides by Spot Test	Pass	Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1
Surface Insulation Resistivity (SIR), Typical	Pass	Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3
		Blank 2220-VF
	Day 1	9.5*10 ⁹ Ω 6.0*10 ⁸ Ω
	Day 4	8.3*10 ⁹ Ω 7.8*10 ⁸ Ω
	Day 7	Blank 2220-VF

FLUX APPLICATION

2220-VF can be applied to circuit boards by a spray, dip, foam or wave process. An air knife after the flux tank is recommended to remove excess flux from the circuit board and prevent dripping on the preheater surface.

PROCESSING GUIDELINES

The optimum preheat temperature for most circuit assemblies is 104 to 116 °C (220 to 240 °F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2 to 4 seconds. The wave soldering speed should be adjusted to accomplish proper preheating and evaporate excess solvent, which could cause splattering. For best results, speeds of 1.1 to 1.8 m/min (3½ to 6 ft/min) are used. The surface tension has been adjusted to help the flux form a thin film on the board surface allowing rapid solvent evaporation.

Elimination of Splattering

Since VOC-free fluxes are water-based, splattering can be a problem. Splattering occurs when water comes in contact with molten solder, so it may be necessary to use forced air to drive off the water. Manufacturers have reported that blowing hot air at 0.28 to 0.85 m³/hr (10 to 30 ft³/hr) greatly assists in drying the water off the circuit boards.

Flux Control

Specific gravity is normally the most reliable method to control the flux concentration. To check concentration, a hydrometer should be used. Control of the flux in the foam flux tank during use is necessary for assurance of consistent flux distribution on the circuit boards. DI water can be used to replace evaporative losses. When excessive debris from circuit boards, such as board fibers and from the airline build up in the flux tank, these particulates will redeposit on the circuit boards which may create a buildup of residues on probe test pins. It is, therefore, necessary to clean the tank and then replenish it with fresh flux when excessive debris accumulates in the flux tank.

Cleaning

No neutralizer, saponifiers or detergents are necessary in the water wash system for complete removal of flux residues. It is not recommended to use high mineral content tap water. Otherwise, tap, deionized or softened water may be used for cleaning. The optimum water temperature is 49 to 60 °C (120 to 140 °F), although lower temperatures may be sufficient.

Storage, Handling and Shelf Life

Because this formulation is water-based, it is subject to freezing. A minimum storage temperature of 4 °C (40 °F) is recommended. If frozen, the 2220-VF is easily reconstituted by stirring at room temperature. Shelf life is 1 year from the date of manufacture when handled properly and held at 4 to 25 °C (40 to 77 °F).

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.