


Ultra Low Dross

Extruded Bar Solder Using Low Dross Technology

Product Description

Kester Ultra Low Dross Bar Solder was developed to provide lower dross in wave solder, selective solder and dip solder processes. This product is a step above our Ultrapure® line of bar solder.

Dross weight comparison



Results are based on an “in-house” experiment using an aerated 2000 gram solder pot at 260 °C (500 °F).

Available Alloys with Low Dross Properties

Sn63Pb37

Process Information

Many solder impurities have been known to contribute to dross formation. Kester Ultra Low Dross integrates low dross technology with Kester’s extruded bar manufacturing process. To minimize oxidation and alloy segregation, Kester pours and quick chills ingots of solder alloy. The ingot is inserted into an airtight hydraulic press which then extrudes bars in a highly efficient and automated manner.

Kester suggests, as with all our products, that this is purchased directly or through stocking distributors. Kester is the only manufacturer of Ultrapure and Ultrapure Low Dross quality solder. Both conform to the requirements of J-STD-006C (formerly QQ-S-571F).

Maximum Allowed Impurities

Ultrasure meets the requirements of current industry standards for allowable impurity requirements.

Element	J-STD-006C	Kester Ultrasure	Ultra Low Dross
Tin	Component	63.500	63.500
Lead	Component	Balance	Balance
Antimony	0.200	0.200	0.050
Copper	0.080	0.080	0.015
Gold	0.050	0.050	0.002
Aluminum	0.005	0.005	0.002
Cadmium	0.002	0.002	0.001
Zinc	0.003	0.003	0.001
Silver	0.100	0.100	0.050
Bismuth	0.100	0.100	0.020
Arsenic	0.030	0.030	0.020
Iron	0.020	0.020	0.010
Indium	0.100	0.100	0.007
Nickel	0.010	0.010	0.002

DOD-STD-2000-1A (Soldering Technology High Quality/High Reliability) states that it is the responsibility of the manufacturer to select those materials and processes that will produce acceptable high quality/high reliability products. Except where otherwise indicated, the component elements in each alloy shall deviate from their nominal mass percentage by not >0.10% of the alloy mass when their nominal percentage is $\leq 1.0\%$; by not > 0.20% of the alloy mass when their nominal percentage is > 1.0% to $\leq 5.0\%$ or by not > 0.50% when their nominal percentage is > 5.0%.

Storage, Handling and Shelf Life

Storage must be in a dry, non-corrosive environment between 10 to 40 °C (50 to 104 °F). The surface may lose its shine and appear a dull shade of grey. This is a surface phenomenon and is not detrimental to product functionality. Solder bar has a limited warranty period determined by the alloy used in the bar. For alloys containing more than 70% lead, the warranty period is 2 years from the date of manufacture. Other alloys have a warranty period of 3 years from the date of manufacture.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

North America 800 West Thorndale Avenue Itasca, IL USA 60143 Phone: +1 800.2.KESTER	Asia Pacific 61 Ubi Avenue 1 #06-01 UB Point Singapore 408941 Phone: +65 6.449.1133	Europe Ganghofer Strasse 45 82216 Gernlinden, Germany Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.