

AW

For Lead-free and Leaded Alloys

Product Description

Kester AW is a highly active inorganic acid type of flux developed for industrial soldering applications where a flux-cored solder wire is desirable. Rapid soldering can be accomplished on all common metals except aluminum and manganese. AW flux is particularly useful for soldering excessively oxidized metals. AW core flux possesses excellent thermal stability to function under prolonged high temperature conditions as with torch or flame soldering. It is not recommended for electrical or electronic soldering applications due to the corrosive nature of the residue

Performance Characteristics:

- Solders excessively oxidized materials
- Not for aluminum or manganese
- Excellent thermal stability
- Compatible with leaded and lead free alloys
- Classified as INH1 per J-STD-004

RoHS Compliance

This product meets the requirements of the RoHS (Restriction of Hazardous Substances) Directive, 2002/95/EC Article 4 for the stated banned substances. (Applies only if this core flux is combined with a lead-free alloy)

Suggested Alloys

50/50 - Tin/Lead

General purpose: For non-electrical applications such as galvanized gutters, sheet metal, radiator repair and stained glass soldering.

95/5 - Tin/Antimony

General purpose: For joining copper tubing in air-conditioning and refrigeration equipment. Also for soldering copper pipe and fittings for drinking water systems.

Availability

AW is available in a wide variety of alloys, wire diameters, flux percentages and roll sizes in both leaded and lead free alloys. Please refer to <https://www.kester.com> for wire diameters, flux percentages and roll sizes that are available.

The standard wire diameter for most applications is 0.8 mm (0.031 in). Wire diameters range from 0.8 to 2.5 mm (0.031 to 0.093 in). The amount of flux in the wire dictates the ease of soldering for an application. For most applications 3.3% flux by weight is recommended. Kester Acid Core is packaged on spools of different sizes to accommodate a variety of applications.

For other alloys and flux percentages, please contact Kester Customer Service. Please refer to <https://www.kester.com> for more information.

Process Considerations

Solder iron tip temperatures are most commonly between 371 to 400 °C (700 to 750 °F) for lead-free alloys and 315 to 343 °C (600 to 650 °F) for leaded alloys. Heat both the land area and component lead to be soldered with the iron tip prior to applying the solder wire to land area or component lead. To maximize tip life and reduce solder spattering, do not feed wire directly to iron tip.

Additional liquid flux should only be used as a last resort. Any flux applied to the solder location should be kept to the area of the connection being reworked. If needed, Kester 1630 Inorganic Acid Flux may be used as a compatible liquid flux to aid in enhancing solderability of soldered joints.

Cleaning

AW possesses excellent fluxing ability, however, flux residue after soldering is hygroscopic and corrosive. The work should be allowed to cool undisturbed until the solder solidifies. The flux residue is then removed with a hot water rinse.

For more thorough cleaning requirements, rinse with a 2 to 10% solution of Kester 5760 Neutralizer followed by a thorough hot water rinse. Please contact Kester Technical Support for further information.

Storage, Handling and Shelf Life

Storage must be in a dry, non-corrosive environment between 10 to 40 °C (50 to 104 °F). The surface may lose its shine and appear a dull shade of grey. This is a surface phenomenon and is not detrimental to product functionality. Flux-cored solder wire has a limited warranty period determined by the alloy used in the wire. For alloys containing more than 70% lead, the warranty period is 2 years from the date of manufacture. Other alloys have a warranty period of 3 years from the date of manufacture.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

Contact Information

To confirm this document is the most recent version, please contact
Assembly@MacDermidAlpha.com

North America 800 West Thorndale Avenue Itasca, IL USA 60143 Phone: +1 800.2.KESTER	Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong Phone: +852.3190.3100	Europe Ganghofer Strasse 45 82216 Gernlinden, Germany Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.