

1630 Soldering Flux

Water Soluble Liquid Flux for Heat Sink Applications

Product Description

Kester 1630 Soldering Flux is a bromide based, chloride-free, inorganic salt activated flux containing less than 1% free acid. 1630 is an excellent flux for soldering copper, brass and all types of tin-based solders from low tin to lead free solders. 1630 has a bromide activator that will not turn copper or brass green during normal soldering operations. 1630 is also used for soldering nickel and mild steel. 1630 was developed for soldering electrical connections like fuses and can be used to solder all copper based alloy joints. The inorganic salt activation system gives 1630 great heat stability over a long period of time using a wide variety of heating techniques.

Performance Characteristics:

- High activity for soldering most metals
- Will not discolor copper and brass
- Excellent heat stability
- Classified as INH1 per IPC J-STD-004

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

Physical Properties

Specific Gravity: 1.087

Anton Paar DMA 35 @ 25 °C

Percent Free Acid (as HBr): 0.50

Availability

1630 is supplied in non-returnable 1, 5 and 53 gallon containers.

Application

1630 is usually applied by brush or dip method at room temperature. If the flux tank is heated, it might be necessary to make water additions to maintain the specific gravity.

Process Considerations

Any machinery or construction materials, which might be exposed to direct contact with the flux, should also be able to withstand strong acids.

Flux Control

1630 can be used as received. No mixing or dilution is required.

Cleaning

Residues from 1630 do not have to be removed from soldering applications depending on the requirements of the operation. Post-soldering residues are water soluble and can be cleaned easily in warm water, if desired.

Storage, Handling and Shelf Life

Shelf life is 3 years from the date of manufacture when handled properly and held at 5 to 45 °C (41 to 113 °F). If the storage temperature exceeds this range, the flux should be brought to room temperature and thoroughly mixed before dilution or use. 1630 should be stored out of direct sunlight. 1630 should be mixed and kept in polyethylene, PVC or fiberglass reinforced polyester containers at all times.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

North America 800 West Thorndale Avenue Itasca, IL USA 60143 Phone: +1 800.2.KESTER	Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong Phone: +852.3190.3100	Europe Ganghofer Strasse 45 82216 Gernlinden, Germany Phone: +49 (0) 8142 4785 0
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "®" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.