

# 955 Soldering Flux Low-Solid No-Clean Liquid Flux for Photovoltaic Assembly

# Product Description

Kester 955 is a low solid, halide-free, non-rosin organic flux designed specifically for use in tabber and stringer equipment of Photovoltaic Assembly (PV) through soldering tabs to cell contacts. 955 can be applied directly to interconnecting ribbon by hand soldering and auto-equipment with tabbing and stringing soldering system. It can be applied by dipping or spraying methods. The extremely low solids content (around 1.5%) and nature of the activator system results in practically no residue left on the cell after soldering. Cells are dry and cosmetically clean as they exit the tabber and stringer machine. 955 has a wide operating window and temperature range. It can be used in SnPb, SnAgPb and Pb-free applications.

#### **Performance Characteristics:**

- Halide-free & low-solid
- Eliminates cleaning process
- Fast throughput due to quick wetting and drying
- Produces high reliable ribbon that interconnects solar cells

**RoHS** Compliance

- Less residue that support higher power transfer efficiencies
- Compatible with EVA
- Classified as ORL0 per J-STD-004 and conforms to Bellcore GR-78 requirement
- Can be applied by using spraying method or via dipping tank
- This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2011/65/EU for the stated banned substances.

Tested by potentiometric titration

KOH/g of flux

## Physical Properties

Appearance: Clear, colorless liquid

Specific Gravity: 0.805 Anton Paar DMA 35 @ 25°C



**Copper Mirror Corrosion:** Pass Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Corrosion Test: Pass Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Acid Number (typical): 10.0 mg

#### Surface Insulation Resistivity (SIR), (typical): Pass Tested to J-STD-004A, IPC-TM-650, Method

Percent Solids (wt/wt): 1.5%

2.6.3.3

	Blank	955
96 hr (ohm)	2.5*10 <sup>10</sup> Ω	2.5*10 <sup>10</sup> Ω
168 hr (ohm)	2.0*10 <sup>10</sup> Ω	2.0*10 <sup>10</sup> Ω

Global Headquarters: 800 West Thorndale Avenue, Itasca, IL USA 60143 • Phone: +1 800.2.KESTER • Fax: +1 630.616.4044 Asia-Pacific Headquarters: 61 Ubi Avenue 1 #06-01 UB Point, Singapore 408941 • Phone: +65 6.449.1133 • Fax: +65 6.242.9036 European Headquarters: Ganghofer Strasse 45, 82216 Gernlinden, Germany ● Phone: +40 (0) 8142 4785 0 • Fax: +40 (0) 8142 4785 61 Asia Manufacturing: Hengqiao Road, Wujiang Economic Development Zone • Suzhou, Jiangsu Province, China 215200 • Phone: +86 512.82060807 • Fax: +86 512.8206 0808 Website: www.kester.com



## ✓Flux Application

Apply a small amount of liquid flux to avoid potential dewetting or residue on the cell.

### Process Considerations

955 is engineered for the PV industry. The chemical flux are to designed for both automated tabber and stringer application, including hand soldering. Standard pre-heating and heat temperature can be used without special cooling or pre-baking. Consult your Equipment Supplier or Kester Technical Support for further information.

# Cleaning

955 flux residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, consult Kester Technical Support for cleaning recommendation.

#### Storage and Shelf Life

955 is flammable. Store away from sources of ignition. Shelf life is 1-year from the date of manufacture when handled properly and held at 10-25°C (50-77°F).

#### $\otimes$ Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet (SDS) and warning label before using this product.