

Test Report Page: 1 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

The following samples was/were submitted and identified by/on behalf of the applicant as:

Sample Submitted By : KESTER LLC Sample Description : 285 - Sn95Sb5 Style/Item No. : 24-7080-9710 Sample Receiving Date: 2019/12/09

Testing Period : 2019/12/09 to 2019/12/16

Test Requested

(1) As specified by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP contents in the submitted sample(s).

(2) Please refer to next pages for the other item(s).

: Please refer to following pages. Test Result(s)

(1) Based on the performed tests on submitted sample(s), the test results of Cadmium, Lead, Conclusion Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP comply with the limits as set by

RoHS Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU.

Signed for and behalf of SGS TAIWAN LTD. Chemical Laboratory - Taipei



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/terms-



Test Report Page: 2 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Test Result(s)

PART NAME No.1 : SILVER COLORED METAL WIRE

Test Item(s)	Unit	Method	MDL	Result No.1	Limit
Lead (Pb)	mg/kg	performed by ICP-OES.	2	242	1000
Mercury (Hg)	mg/kg	With reference to IEC 62321-4:2013+ AMD1:2017 and performed by ICP-OES.	2	n.d.	1000
Hexavalent Chromium Cr(VI)(#2)	μg/cm²	With reference to IEC 62321-7-1 (2015) and performed by UV-VIS.	0.10	n.d.	-
Sum of PBBs	mg/kg		-	n.d.	1000
Monobromobiphenyl	mg/kg		5	n.d.	-
Dibromobiphenyl	mg/kg		5	n.d.	-
Tribromobiphenyl	mg/kg]	5	n.d.	-
Tetrabromobiphenyl	mg/kg	With reference to IEC 62321-6 (2015) and performed by GC/MS.	5	n.d.	-
Pentabromobiphenyl	mg/kg		5	n.d.	-
Hexabromobiphenyl	mg/kg		5	n.d.	-
Heptabromobiphenyl	mg/kg		5	n.d.	-
Octabromobiphenyl	mg/kg		5	n.d.	-
Nonabromobiphenyl	mg/kg		5	n.d.	-
Decabromobiphenyl	mg/kg		5	n.d.	-
Sum of PBDEs	mg/kg		-	n.d.	1000
Monobromodiphenyl ether	mg/kg		5	n.d.	-
Dibromodiphenyl ether	mg/kg		5	n.d.	-
Tribromodiphenyl ether	mg/kg		5	n.d.	-
Tetrabromodiphenyl ether	mg/kg		5	n.d.	-
Pentabromodiphenyl ether	mg/kg		5	n.d.	-
Hexabromodiphenyl ether	mg/kg		5	n.d.	-
Heptabromodiphenyl ether	mg/kg		5	n.d.	-
Octabromodiphenyl ether	mg/kg		5	n.d.	-
Nonabromodiphenyl ether	mg/kg		5	n.d.	-
Decabromodiphenyl ether	mg/kg		5	n.d.	-



Test Report Page: 3 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Test Item(s)	Unit	Method	MDL	Result	Limit
DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7)	mg/kg	With reference to IEC 62321-8 (2017). Analysis was performed by GC/MS.	50	No.1 n.d.	1000
BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)	mg/kg		50	n.d.	1000
DBP (Dibutyl phthalate) (CAS No.: 84-74-2)	mg/kg		50	n.d.	1000
DIBP (Di-isobutyl phthalate) (CAS No.: 84-69-5)	mg/kg		50	n.d.	1000
DIDP (Di-isodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1)	mg/kg		50	n.d.	-
DINP (Di-isononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0)	mg/kg		50	n.d.	-
DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)	mg/kg		50	n.d.	-
Halogen					
Halogen-Fluorine (F) (CAS No.: 14762-94-8)	mg/kg	With reference to BS EN 14582 (2016). Analysis was performed by IC.	50	n.d.	-
Halogen-Chlorine (CI) (CAS No.: 22537-15-1)	mg/kg		50	n.d.	-
Halogen-Bromine (Br) (CAS No.: 10097-32-2)	mg/kg		50	62.6	-
Halogen-lodine (I) (CAS No.: 14362-44-8)	mg/kg		50	n.d.	-

Note:

- 1. mg/kg = ppm; 0.1wt% = 1000ppm
- 2. MDL = Method Detection Limit
- 3. n.d. = Not Detected = less than MDL
- 4. " " = Not Regulated
- 5. (#2) =
 - a. The sample is positive for Cr(VI) if the Cr(VI) concentration is greater than 0.13 µg/cm². The sample coating is considered to contain Cr(VI)
 - b. The sample is negative for Cr(VI) if Cr(VI) is n.d. (concentration less than 0.10 µg/cm²). The coating is considered a non-Cr(VI) based coating
 - c. The result between 0.10 µg/cm² and 0.13 µg/cm² is considered to be inconclusive unavoidable coating variations may influence the determination.
- This report supersedes the previous document bearing the test report number CE/2019/C0994A.



Test Report No.: CE/2019/C0994B Page: 4 of 8 Date: 2020/03/05


KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Analytical flow chart of Heavy Metal

These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr⁶⁺ test method excluded)

Technician : Rita Chen Supervisor: Troy Chang





Test Report Page: 5 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Analytical flow chart - PBB / PBDE

Technician: Yaling Tu

First testing process -

Optional screen process •••• Confirmation process

Supervisor: Troy Chang Sample Sample pretreatment Screen analysis Sample extraction / Soxhlet method Concentrate/Dilute Extracted solution • Filter GC/MS



Test Report Page: 6 of 8 No.: CE/2019/C0994B Date: 2020/03/05


KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Analytical flow chart - Phthalate

Technician: Yaling Tu Supervisor: Troy Chang

[Test method: IEC 62321-8]






Test Report Page: 7 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

Analytical flow chart - Halogen

Technician: Rita Chen Supervisor: Troy Chang






Test Report Page: 8 of 8 No.: CE/2019/C0994B Date: 2020/03/05

KESTER LLC

800 W. THORNDALE AVE. ITASCA, IL 60143

* The tested sample / part is marked by an arrow if it's shown on the photo. *

CE/2019/C0994



** End of Report **